

Declaration of Performance

No. 001DoP-CDC-B1a

- 1: **Unique identification code of the product type** : Dry-Pressed ceramic tiles, with water absorption $E_b \leq 0,5\%$.
- 2: **Intended use** : For internal and external walls and floorings.
- 3: **Name or registered trade mark, and contact address of the manufacturer** : Ceramica del Conca S.p.a. - Via Croce, 8 – 47832 San Clemente (RN) - Italia
- 4: **System of assessment and verification of constancy of performance (AVCP)** : 4
- 5: **Name and identification number of notified laboratory, if relevant**: not applicable
- 6: **Declared performance**:

<u>Essential Characteristics</u>	<u>Performance</u>	<u>Harmonized Technical Specification</u>
Reaction to fire	A1 - A1 _{FL}	EN 14411:2012
Release of dangerous substance, for		
Cadmium	NPD	
Lead	NPD	
Breaking Strength:	> 1300 N	
Slipperiness	See table attached	
Tactility	NPD	
Bond strength/adhesion for:		
Cementitious adhesive, type C2	1 N/mm ²	
Thermal shock resistance	Pass	
Durability		
Internal use:	Pass	
External use: (freeze-thaw resistance)	Pass	

The performance of the product identified in point 1 is in conformity with the declared performance in point 6.
This declaration of performance is issued under the sole responsibility of the manufacturer identified in point 3.

Signed for and on behalf of the manufacturer by: Luca Costi Technical Director

Place and date of issue

San Clemente, 02/08/17

Signature


CERAMICA DEL CONCA SpA
47832 - SAN CLEMENTE (RN) Italy
Fraz. Sant'Andrea in Casale
Cod. Fisc. e P. IVA: 00819720400
Tel. 0541-988453 - Fax 0541-988783

This document of performance does not include decorative accessories, trim and mosaic.

		DIN51130	DIN51097	ANSI 137.1 (DCOF)			
				BCRA			
				bagnato/wet	asciutto/dry	bagnato/wet	
Porcellana d'arredo	HZG - Zelo Grip	R13	C	≥0,42	>0,40	>0,40	
	KY	R9	-	≥0,42	>0,40	>0,40	
Rover	O	-	A	-	-	-	
	TE - Terminus	R9*	B*	≥0,42*	>0,40*	>0,40*	
	AR - Artelegno	R9*	B*	≥0,42*	>0,40*	>0,40*	
	DL - Dolomiti	R10	B	≥0,42	>0,40	>0,40	
	DG - Dolomiti Grip	R12	C	≥0,42	>0,40	>0,40	
	DV - Da Vinci	R10	B	≥0,42	>0,40	>0,40	
	EK - Epokal	R9*	B*	≥0,42*	>0,40*	>0,40*	
	LB - Bosco di Casole	R9	B	≥0,42	>0,40	>0,40	
	LF - In Out	R10	B	≥0,42	-	>0,40	
	LG - In Out Grip	R12	C	≥0,42	>0,40	>0,40	
	LM - Montenapoleone	R9	B	≥0,42	>0,40	>0,40	
	FI - Foreste d'Italia	R9	B	≥0,42	>0,40	>0,40	
	FG - Foreste d'Italia Grip	R12	C	≥0,42	>0,40	>0,40	
	GP - Gran Paradiso	R9	B	≥0,42	>0,40	>0,40	
	MN - Monteverde	R9	B	≥0,42	>0,40	>0,40	
	MG - Monteverde Grip	R12	C	≥0,42	>0,40	>0,40	
SA - Saloon	R9	B	≥0,42	>0,40	>0,40		
VW - Vignoni wood	R10	A	≥0,42	>0,40	>0,40		
Fast	LM FAST	R9	B	≥0,42	>0,40	>0,40	
	HFO FAST	R9	A	≥0,42	>0,40	>0,40	
	SA FAST	R9	B	≥0,42	>0,40	>0,40	
	HAL - Halo	R9	B	≥0,42	>0,40	>0,40	
	HBO - Blue Quarry	R9	B	≥0,42	>0,40	>0,40	
Hard	HCL - Climb	R10	B	≥0,42	>0,40	>0,40	
	HCL - Climb grip	R12	C	≥0,42	>0,40	>0,40	
	HCP - Les Baux de Provence	R11	A	≥0,42	>0,40	>0,40	
	HDG - Dogma	R9*	B*	≥0,42*	>0,40*	>0,40*	
	HDT - Docet	R9*	B*	≥0,42*	>0,40*	>0,40*	
	HEG - Engadina	R9	B	≥0,42	>0,40	>0,40	
	HGA - GA by Giugiaro	R9	B	≥0,42	>0,40	>0,40	
	HGT - Galestro	R11	C	≥0,42	>0,40	>0,40	
	HMC - Mulini di Canepa	R11	B	≥0,42	>0,40	>0,40	
	HNT - Nat	R11	B	≥0,42	>0,40	>0,40	
	HPE - Hyper	R11	C	≥0,42	>0,40	>0,40	
	HPR - Pietra Regia	R11	C	≥0,42	>0,40	>0,40	
	HRC	R10	-	≥0,42	>0,40	>0,40	
	HRK - Rustiko	R12	C	≥0,42	>0,40	>0,40	
	HRI - Rock Island	R11	B	≥0,42	>0,40	>0,40	
	HRN - Carnegna	R9	-	≥0,42	>0,40	>0,40	
	HRT - Rockstar	R12	C	≥0,42	>0,40	>0,40	
	HSC - Stone Capital	R10	B	≥0,42	>0,40	>0,40	
	HSC - Stone Capital Grip	R12	C	≥0,42	>0,40	>0,40	
	HSF - Sassofeltrò	R9	-	≥0,42	>0,40	>0,40	
	HSU - Soul	R10*	B*	≥0,42*	>0,40*	>0,40*	
	HTV - Tivoli	R9	-	≥0,42	>0,40	>0,40	
	HUP - Upgrade	R10	B	≥0,42	>0,40	>0,40	
	HVG - Vignoni (15x30)	R10	B	≥0,42	>0,40	>0,40	
	HVG - Vignoni	R9	A	≥0,42	>0,40	>0,40	
	Contract	HEM - Elementi	-	B	≥0,42	>0,40	>0,40
		HEV - Evolution	-	-	≥0,42	>0,40	>0,40
HEV grip		R10	B	≥0,42	>0,40	>0,40	
HEX - Experience		-	A	≥0,42	-	-	
HFO - Forma		R9	A	≥0,42	>0,40	>0,40	
HPV - Pienza		R11	B	≥0,42	>0,40	>0,40	
HIM - Fori Imperiali		R9	B	≥0,42	>0,40	>0,40	
HIM Grip - Fori Imperiali		R11	C	≥0,42	>0,40	>0,40	
HAV2		R11	C	≥0,42	>0,40	>0,40	
HBO2		R11	C	≥0,42	>0,40	>0,40	
Duc	HBP205	R11	C	≥0,42	>0,40	>0,40	
	HBP208	R11	C	≥0,42	>0,40	>0,40	
	HBO2	R12	C	≥0,42	>0,40	>0,40	
	HCL2	R11	C	≥0,42	>0,40	>0,40	
	HDG2	R11	C	≥0,42	>0,40	>0,40	
	HDL2	R11	C	≥0,42	>0,40	>0,40	
	HDV2	R11	C	≥0,42	>0,40	>0,40	
	HED2	R11	C	≥0,42	>0,40	>0,40	
	HEG2	R11	C	≥0,42	>0,40	>0,40	
	HEK2	R11	C	≥0,42	>0,40	>0,40	
	HFR2	R11	C	≥0,42	>0,40	>0,40	
	HMN2	R11	C	≥0,42	>0,40	>0,40	
	HNT2	R12	C	≥0,42	>0,40	>0,40	
	HPR2	R12	C	≥0,42	>0,40	>0,40	
	HRV2	R11	C	≥0,42	>0,40	>0,40	
	HSA2	R11	C	≥0,42	>0,40	>0,40	
	HSC2	R11	C	≥0,42	>0,40	>0,40	
	HSU2	R12	C	≥0,42	>0,40	>0,40	
	HTE2	R11	C	≥0,42	>0,40	>0,40	
	HUP2	R11	C	≥0,42	>0,40	>0,40	
	HQZ2	R11	C	≥0,42	>0,40	>0,40	
	HVG2	R11	C	≥0,42	>0,40	>0,40	
	Surface	HPA Pandora	R10	B	≥0,42	>0,40	>0,40
OB Orto Botanico		R9	B	≥0,42	>0,40	>0,40	
HBO - Boutique		R9*	B*	≥0,42*	>0,40*	>0,40*	
HAV - Anversa		R10	B	≥0,42	>0,40	>0,40	
SR - St. Regis		R9	B	≥0,42	>0,40	>0,40	
Plus	EB						
	JS						
	MR						
	MV						
	PL						
	TR						

*Excluso Shine - *Except for Shine